



Microcontainers - an oral drug delivery system for poorly soluble drugs

Nielsen, Line Hagner; Petersen, Ritika Singh; Marizza, Paolo; Keller, Stephan Sylvest; Melero, A.; Rades, T.; Müllertz, A.; Boisen, Anja

Publication date:
2016

Document Version
Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):
Nielsen, L. H., Petersen, R. S., Marizza, P., Keller, S. S., Melero, A., Rades, T., Müllertz, A., & Boisen, A. (2016). *Microcontainers - an oral drug delivery system for poorly soluble drugs*. Poster session presented at 11th International Conference and Workshop on Biological Barriers, Saarbrücken, Saarland, Germany.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

Please create your abstract using the following template and send the document as pdf-file to
Biobarriers2016@mx.uni-saarland.de

Please do not modify the format of this template! Abstract limit is 1 page A4.

NOTE: Please save your abstract file according to the name of the presenting author as a 'pdf' file
(Author A B.pdf).

Microcontainers - an oral drug delivery system for poorly soluble drugs

Hagner Nielsen L.¹, Petersen R.S.¹, Marizza P.¹, Keller S.S.¹, Melero A.², Rades T.³, Müllertz A.³, Boisen A.¹

¹Department of Micro and Nanotechnology, Technical University of Denmark, Kgs. Lyngby, Denmark

²Department of Pharmacy and Pharmaceutical Technology, University of Valencia, Valencia, Spain

³Department of Pharmacy, Faculty of Health and Medical Sciences, University of Copenhagen, Copenhagen, Denmark

In oral delivery, it can sometimes be necessary to employ drug delivery systems to achieve targeted delivery to the intestine. Microcontainers are polymeric, cylindrical devices in the micrometer size range (Figure 1), and are suggested as a promising oral drug delivery system [1],[2]. The purpose of these studies was to fabricate microcontainers in either SU-8 or biodegradable poly-L-lactic acid (PLLA), and fill the microcontainers with poorly soluble drugs. Furthermore, the application of the microcontainers as an oral drug delivery system was investigated in terms of release, *in situ* intestinal perfusion and oral bioavailability.

SU-8 microcontainers were fabricated using lithography resulting in microcontainers with an inner diameter of 220 μm . The PLLA microcontainers were prepared by hot embossing with inner diameter of 240 μm (Figure 1). In terms of drug filling, the SU-8 microcontainers were filled with polyvinylpyrrolidone (PVP) by inkjet printing followed by supercritical CO_2 impregnation of ketoprofen into the PVP matrix. As an alternative filling method, the powder of amorphous sodium salt of furosemide, (ASSF) was filled into the SU-8 microcontainers. The PLLA microcontainers were filled with drug formulation by embossing the microcontainers into a polycaprolactone (PCL) and furosemide (4:1 w/w) layer. For the ASSF-filled microcontainers, an enteric-resistant lid of Eudragit L100 was spray coated onto the cavity of the microcontainers. From coated ASSF-filled microcontainers, a fast release in simulated intestinal medium at pH 6.5 was observed. *In situ* intestinal perfusions were performed in rats of the Eudragit-coated ASSF-filled microcontainers and compared to a furosemide solution. At the end of the study, the small intestine was harvested from the rat and imaged under a light microscope. The absorption rate constant of ASSF was 1.5 fold higher, when ASSF was confined in the microcontainers compared to a furosemide solution. Micrographs of the small intestine after the perfusion showed that the microcontainers were engulfed by the intestinal mucus. For the *in vivo* studies, the rats were dosed orally with capsules containing ASSF-filled microcontainers coated with Eudragit L100. As control, capsules were filled with the powder of ASSF and the capsules were coated with Eudragit L100. The oral bioavailability study showed that the relative oral bioavailability of ASSF in microcontainers is $220 \pm 43\%$ when compared to drug-filled capsules coated with Eudragit (Figure 2).




Figure 1: SEM images of SU-8 (left) and PLLA (right) microcontainers




Figure 2: Plasma concentrations of microcontainers filled with ASSF coated with Eudragit L100 and filled into capsules and ASSF dosed in capsules with Eudragit coating after orally dosing to rats

Acknowledgments: The authors would like to acknowledge the Danish Research Council for Technology and Production (FTP), Project DFF - 4004-00120B for financial support. Moreover, the Danish National Research Foundation, project: DNRD122 is acknowledged.

References:

1. Chirra, HD. et. al.: Adv. Healthc. Mater. **2014**, 3: 1648–1654.
2. Nielsen, LH. et al.: Eur J Pharm and Biopharm. **2012**, 81: 418-25.